

Technical Data Sheet

AF63**/00 CLEAR WATERBORNE SELF-SEALER FOR PARQUET FLOORING

Supersedes previous issue dated 13.03.18

DATE 05/December/18

Gloss:	5, 10, 20, 30, 50, 80 gloss.
Area of use:	Specifically formulated for parquet floors.
Method of use:	Spray and brush: ready to use. Roller: thin 10% with drinking water.

Technical characteristics

Solids content (%):	31 ± 2
Specific gravity (kg/l):	1.040 ± 0.030
Viscosity (DIN 4 at 20°C):	40" ± 3" (50" ± 4" for 80 gloss version)

General characteristics

Drying time (80 g/m ² at 20°C 65% humidity):	Dust free	15' - 20'
	Touch dry	30' - 40'
	Sandable:	2 hours
	Overcoatable:	2 hours
	Foot traffic:	24 hours
Recommended application weight (g/m ²):	Min. 60, Max. 100	
Number of coats:	Max. 3.	
Shelf-life (months):	15	

AF63**/00 is a one-pack clear waterborne self-sealer for use on parquet flooring. For its characteristics of elasticity and surface hardness, this product has good chemical-physical resistances.

It has excellent defoaming properties in application by roller and brush.

In spray application there are no problems of adhesion between coats.

It has excellent transparency even at low gloss.

It can be applied without a barrier basecoat in first-hand on oily or resinous woods. However we recommend a check before starting work.

Its formula guarantees the absence of risk phrases on the label.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

COMPANY WITH
MANAGEMENT SYSTEM
- UNI EN ISO 9001 -
- UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio
Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770 511 - fax +39 051 777 437
www.sayerlack.com
Cod. Fisc. e Reg. Impr. Bo 08866930152
P. IVA: IT 00494251200 - R.E.A. n. 313180
Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA



It is recommended for floors for residential use

Method of use

On untreated surfaces fill any cracks using AF63**/00 mixed with the sawdust obtained by wood floor smoothing. To facilitate the processability of the obtained paste dilute with some water

When the filler has dried, sand the floor carefully using 80-120 grit sandpaper. Remove the sanding dust with a vacuum cleaner before applying the coating.

Apply the first coat of AF63**/00 using a roller or a brush. Make sure that the product is well spread and there are no areas of build-up.

After about 1 hour, when drying is complete, first layer of product is ready for sanding. It is preferable to sand manually using 150-180 grit paper or with mechanical systems using 220-240 grit paper. Then apply a second coat and after about 2 hours sand with 240-320 grit paper and apply third coat.

Do not allow the product to build up in any areas and make sure that it is spread uniformly and with the recommended application weight of about 70-80 g/m² for each coat. This can easily be achieved using normal brush application. Higher application weights require much longer drying times.

How to clean and maintain

To clean the floor coated with AF63**/00 the use of a soft cloth with water and neutral soap is recommended.

Avoid the use of detergents and waxes that contain aggressive solvents.

In case of maintenance sand well the floor using 150 grit sandpaper, then remove the majority of dirt, dust and sand. Apply one or two coats of AF63**/00 as described in TDS.

Special instructions

Accidental application of thick layers of product may cause spots and cissing and slow down drying to such an extent that the film lifts from the wood.

Keep from freezing: store in areas where temperatures do not fall below 5°C.

During application and drying, the ambient temperature and the temperature of the coating must be no lower than 10°C.

Use only drinking water for thinning.

Mix the product using a stick or a spatula. Avoid stirring too vigorously not to incorporate air in the product which may lead to the formation of bubbles during application.

Ventilate the room during and after application to improve drying.

The coated floor is ready for foot traffic the next day.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.
WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

COMPANY WITH
MANAGEMENT SYSTEM
- UNI EN ISO 9001 -
- UNI EN ISO 14001 -

Sherwin-Williams Italy S.r.l. – con unico socio
Via del Fiffo, 12 - 40065 Pianoro (BO) - Italia - C.P. 18
tel. +39 051 770 511 - fax +39 051 777 437
www.sayerlack.com
Cod. Fisc. e Reg. Impr. Bo 08866930152
P. IVA: IT 00494251200 - R.E.A. n. 313180
Cap. Soc. Euro 2.626.182 I.V. - Codice Mecc. Bo 014531

Company under the direction and coordination of The Sherwin-Williams Company, USA

After application wait 48-72 hours before placing furniture or carpets on the floor.

For the first 2-3 weeks the coating is not perfectly dry and remains slightly sensitive to water. If the floor is washed and/or water deposits in some areas after treatment, this may give rise to reversible blooming on the film of coating.

Wash working tools immediately with water. Dried coating can be removed by washing with acetone.

Coating residues must be disposed of in accordance with current legislation. Do not pour residues down drains.

Due to the great number of exotic timbers available on the market, it is advisable to perform a preliminary test to verify that the product does not undergo cissing, blushing or lifting caused by substances contained in the wood.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.