

## Technical Data Sheet

**ES52**

10/10/2016

**Version 1**

SIRCA S.p.A. - Offices and plant: Viale Roma, 85-35010 San Dono di Massanzago (PD) - Italy - Tel. 049/9322311 ra - 049/5797262 Fax - Internet: www.sirca.it.

S.p.A. has a quality system certified by DNV according to standard UNI EN ISO 9001.

### Name and Code

ES52 .

### Chemical Nature

Polyisocyanic hardener.

### Description and performances

Hardener for PU and acrylic coatings that gives great elasticity and scratch resistance.

### Additional description of the product

#### Chemical - Technical Properties

Description	Method	Unit of measure	Value - Range
Specific gravity	I.O. 309	g/cm <sup>3</sup>	0,930±0,010
Solid content	I.O. 371	%	31±1

### Storage instructions

Keep the product in a ventilated area; do not exceed 25-28 °C. Polyisocyanic hardeners should be protected from frost and humidity. If they have been partially used please close the can tight and use the residual amount in a short time.

EXPIRATION DATE 12 months

The data refers to the product stored in original sealed packaging.

---

## Technical Data Sheet

**ES52**

10/10/2016

*Version*      **1**

---

### **Danger level for people and environment**

Before use consult the safety data sheet

---

The information supplied are correct to the best of our knowledge. However, as the coating process depends on many variables and the present application takes place without our supervision, we cannot assume any responsibility for the final result. Sirca guarantees that chemical and physical characteristics of the products are within the reported range. Due to the large variety of substrates and application devices, the purchaser/user should test our products in his own application conditions and safety and environment circumstances. Sirca's technical and sales departments are at customer's disposal for any further information regarding correct application of our products